

FORM PTO-1390 (Modified)
(REV 10-95)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

199621US0PCT

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR

09/701564

INTERNATIONAL APPLICATION NO.
PCT/EP99/03705INTERNATIONAL FILING DATE
28 MAY 1999PRIORITY DATE CLAIMED
08 JUNE 1998

TITLE OF INVENTION

WATER-ABSORBING POLYMERS HAVING SUPRAMOLECULAR HOLLOW MOLECULES, A METHOD OF
PRODUCING SAME, AND THEIR USE

APPLICANT(S) FOR DO/EO/US

Christoph BRUHN, et al.

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
 - a. ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☒ has been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. ☒ A copy of the International Search Report (PCT/ISA/210).
8. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
9. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
10. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
11. ☐ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
12. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).

Items 13 to 18 below concern document(s) or information included:

13. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☒ A **FIRST** preliminary amendment.
A **SECOND** or **SUBSEQUENT** preliminary amendment.
16. ☐ A substitute specification.
17. ☐ A change of power of attorney and/or address letter.
18. ☐ Certificate of Mailing by Express Mail
19. ☒ Other items or information:

Request for Consideration of Documents Cited in International Search Report

Notice of Priority

PCT/IB/304

PCT/IB/308

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR 1.53) 09/701564	INTERNATIONAL APPLICATION NO. PCT/EP99/03705	ATTORNEY'S DOCKET NUMBER 199621USOPCT
--	---	--

20. The following fees are submitted:

BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :

- | | |
|--|-----------|
| <input checked="" type="checkbox"/> Search Report has been prepared by the EPO or JPO | \$860.00 |
| <input type="checkbox"/> International preliminary examination fee paid to USPTO (37 CFR 1.482) | \$690.00 |
| <input type="checkbox"/> No international preliminary examination fee paid to USPTO (37 CFR 1.482) but international search fee paid to USPTO (37 CFR 1.445(a)(2)) | \$710.00 |
| <input type="checkbox"/> Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO | \$1000.00 |
| <input type="checkbox"/> International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(2)-(4) | \$100.00 |

ENTER APPROPRIATE BASIC FEE AMOUNT =**CALCULATIONS PTO USE ONLY**

\$ 860.00

 Surcharge of \$130.00 for furnishing the oath or declaration later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492 (e)).

0.00

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE
Total claims	21 - 20 =	1	x \$18.00
Independent claims	1 - 3 =	0	x \$80.00
Multiple Dependent Claims (check if applicable).			<input type="checkbox"/>

18.00

0.00

0.00

TOTAL OF ABOVE CALCULATIONS =

\$ 878.00

Reduction of 1/2 for filing by small entity, if applicable. Verified Small Entity Statement must also be filed (Note 37 CFR 1.9, 1.27, 1.28) (check if applicable).

☐

0.00

SUBTOTAL =

\$ 878.00

 Processing fee of \$130.00 for furnishing the English translation later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492 (f)).

+

0.00

TOTAL NATIONAL FEE =

\$ 878.00

Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) (check if applicable).

☐

0.00

TOTAL FEES ENCLOSED =

\$ 878.00

Amount to be:**refunded**

\$

charged

\$

☒ A check in the amount of \$ 878.00 to cover the above fees is enclosed.
☐ Please charge my Deposit Account No. _____ in the amount of _____ to cover the above fees.
 A duplicate copy of this sheet is enclosed.

☒ The Commissioner is hereby authorized to charge any fees which may be required, or credit any overpayment to Deposit Account No. **15-0030** A duplicate copy of this sheet is enclosed.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

**22850**
 Surinder Sachar
 Registration No. 34,423

SIGNATURE

Norman F. Oblon

NAME

24,618

REGISTRATION NUMBER

DEC. 7 2000

DATE

09/701564

199621US0PCT

JC01 Rec'd PCT/PTO 07 DEC 2000

IN THE UNITED STATES PATENT & TRADEMARK OFFICE

IN RE APPLICATION OF :
CHRISTOPH BRUHN ET AL : ATTN: APPLICATION DIVISION
SERIAL NO: NEW U.S. PCT APPLN :
(Based on PCT/EP99/03705)
FILED: HEREWITH :
FOR: WATER-ABSORBING POLYMERS:
WITH SUPRAMOLECULAR
HOLLOW MOLECULES, METHOD
FOR PRODUCING THEM AND
USE OF THE SAME

PRELIMINARY AMENDMENT

ASSISTANT COMMISSIONER FOR PATENTS
WASHINGTON, D.C. 20231

SIR:

Prior to examination on the merits, please amend the above-identified application as follows.

IN THE SPECIFICATION

Please amend the specification as follows:

Page 1, before, line 1, delete the title of the invention in its entirety, and insert therefor:

--WATER-ABSORBING POLYMERS WITH SUPRAMOLECULAR HOLLOW
MOLECULES, METHOD FOR PRODUCING THEM AND USE OF THE SAME--

Page 22, line 16, replace "mm" with -- μ m--.

Page 23, line 16, replace "mm" with -- μ m--.

09/701564-120700

IN THE CLAIMS

Please amend the claims as follows:

--1. (Amended) An absorbent polymer based on optionally partially neutralized, monoethylenically unsaturated monomers bearing acid groups, the surface of which polymer has been subjected to secondary crosslinking subsequent to polymerizing, [characterized in that] wherein the polymer has cyclodextrins and/or cyclodextrin derivatives bound covalently and/or tonically and/or incorporated therein.

2. (Amended) The polymer according to claim 1, [characterized in that] wherein the polymer includes from 0.01 to 50 wt.-%[, preferably from 0.1 to 30 wt.-%, more preferably from 0.5 to 10 wt.-%] of cyclodextrins and/or cyclodextrin derivatives, relative to the polymer.

3. (Amended) The polymer according to claim 1 [or 2, characterized in that] , wherein a maximum of 85 wt.-% of the amount of cyclodextrins and/or cyclodextrin derivatives in the polymer is extractable with water.

4. (Amended) The polymer according to claim 3, [characterized in that] wherein the [extractable amount] amount extractable with water is 60 wt.-% at maximum[, preferably 45% at maximum].

5. (Amended) The polymer according to [any of claims 1 to 4, characterized in that] Claim 1, wherein the polymer is constituted up to 40 wt.-% of monoethylenically unsaturated monomers other than the monomers bearing acid groups.

6. (Amended) The polymer according to [any of claims 1 to 5, characterized in that] Claim 1, wherein the polymer has from 0.05 to 3 wt.-% of a crosslinking monomer incorporated by polymerization.

7. (Amended) The polymer according to [any of claims 1 to 6, characterized in that] Claim 1, wherein the polymer has 30 wt.-% of a water-soluble, natural or synthetic polymer incorporated therein by polymerization and/or graft polymerization.

8. (Amended) The polymer according to [any of claims 1 to 7, characterized in that] Claim 1, wherein the polymer has been subjected to surface crosslinking using from 0.1 to 10 wt.-%, relative to the polymer, of a crosslinker component.

9. (Amended) The polymer according to [any of claims 1 to 8, characterized in that] Claim 1, wherein the polymer contains α -, β -, or γ -cyclodextrins or derivatives thereof as cyclodextrins or derivatives thereof.

10. (Amended) The polymer according to [any of claims 1 to 9, characterized in that] Claim 1, wherein the cyclodextrins or cyclodextrin derivatives are covalently bound to the polymer via ethylenically unsaturated groups.

11. (Amended) The polymer according to [any of claims 1 to 9, characterized in that] Claim 1, wherein the cyclodextrins or cyclodextrin derivatives are tonically bound to the polymer via carboxylate, sulfate, sulfonate, or quaternary amino groups.

12. (Amended) The polymer according to claim 11, [characterized in that] wherein the cyclodextrins or cyclodextrin derivatives are bound to the polymer in a cationic fashion.

13. (Amended) A process for producing the polymers according to [any of claims 1 to 12] Claim 1 by free-radical polymerization of an aqueous solution of the ethylenically unsaturated, optionally partially neutralized monomer bearing acid groups, optionally up to 40 wt.-% of further monoethylenically unsaturated comonomers, crosslinking monomers, and optionally up to 30 wt.-% of a water-soluble natural or synthetic polymer, optional isolation, crushing, and drying of the polymer, [characterized in that] wherein the cyclodextrin and/or cyclodextrin derivative is already contained in the polymer during secondary surface

crosslinking of same, or the polymer having undergone surface crosslinking is treated with an ionic cyclodextrin derivative.

14. (Amended) The process according to claim 13, [characterized in that] wherein the cyclodextrin and/or cyclodextrin derivative is incorporated prior to or during polymerization of the monomers and/or applied on an optionally obtained hydrogel and/or on optionally milled and dried polymer prior to or during surface crosslinking of the polymer.

15. (Amended) The process according to [any of claims 13 to 14, characterized in that] Claim 13, wherein the cyclodextrin or cyclodextrin derivative is employed as substance or as a solution.

16. (Amended) Use of the polymers according to a[ny of claims 1 to 12] Claim 1 as an absorbent for aqueous liquids, preferably in absorbing body fluids, in optionally foamed sheet materials, in packaging materials, in plant breeding, and as soil improver.

17. (Amended) The use of polymers according to claim 16 in hygiene articles.

18. (Amended) Use of the polymers according to [any of claims 1 to 12] Claim 1 as a vehicle and/or stabilizer for active substances or fertilizers being released optionally in a delayed fashion.

Please add the following claims:

--19. The polymer according to Claim 2, wherein the polymer comprises from 0.1 to of cyclodextrins, and/or cyclodextrin derivatives relative to the polymer.

20 The polymer according to Claim 2, wherein the polymer comprises from 0.5 to 10 wt.-% of cyclodextrins, and/or cyclodextrin derivatives relative to the polymer.


21. The polymer according to Claim 4, wherein the amount extractable with water is 45% at maximum.--

REMARKS

Claims 1-21 are active in the present application. The claims are amended for clarity and to remove multiple dependencies The specification is amended to correct a clerical error. Support for Claims 19-21 is found in Claims 2 and 4. No new matter is added. An action on the merits and allowance of the claims is solicited.

Respectfully submitted,

OBLON, SPIVAK, McCLELLAND,
MAIER & NEUSTADT, P.C.



Norman F. Oblon
Attorney of Record
Registration No. 24,618

Daniel J. Pereira, Ph.D.
Registration No. 45,518



22850

(703) 413-3000

Fax #: (703)413-2220

DJPER/la

I:\user\DJPER\199621.pr

**Water-absorbing Polymers Having Supramolecular
Hollow Molecules, a Method of Producing Same, and Their Use**

The invention relates to absorbents, preferably for water and aqueous liquids, which absorbents are based on polymers absorbing aqueous liquids, wherein cyclodextrin or cyclodextrin derivatives have been incorporated ionically, covalently and/or as a result of mechanical inclusion.

Commercially available superabsorbing polymers essentially are crosslinked polyacrylic acids, crosslinked starch-/acrylic acid graft copolymers, crosslinked hydrolyzed starch/acrylonitrile graft copolymers, crosslinked poly-(maleic anhydride-co-isobutylene), or mixtures of various of the above-mentioned crosslinked polymers, wherein the carboxylic groups have been subjected to partial neutralization with sodium and/or potassium ions.

Such polymers find use e.g. in hygiene articles capable of absorbing body fluids such as urine or in materials for cable sheathings where they absorb large amounts of aqueous liquids and body fluids such as urine or blood with swelling and formation of hydrogels. Furthermore, the absorbed amount of liquid must be retained under a pressure typical of use. During the further technical development of superabsorbing polymers, the pattern of requirements to be met by these products has changed significantly over the years. To date, the development of superabsorbers has been forced particularly with respect to the amount of absorbed liquid and pressure stability.

Such crosslinked polymer products based on monomers containing acid groups are obtained by using one or more primary crosslinkers and one or more secondary crosslinkers

09/701564-120700

and exhibit a combination of properties, namely, high retention, high absorption under pressure, low solubles, and rapid absorption of liquid, which has not been achieved so far. When used in hygiene articles, these crosslinked polymer products have the advantage that secreted fluids, once absorbed by the polymer product, can no longer contact the skin. Thus, skin lesions such as diaper dermatitis can largely be avoided. Such comfort can even be increased by absorbing malodorous compounds.

According to Römpp Chemie Lexikon, the content of urine components is subject to physiological fluctuations; also, particular substances are secreted at concentrations varying within a daily period, so that more precise data on the urine composition invariably are related to the so-called 24 hour urine which, in a healthy adult, contains e.g. urea (average 20 g), uric acid (0.5 g), creatinine (1.2 g), ammonia (0.5 g), amino acids (2 g), proteins (60 mg), reducing substances (0.5 g, about 70 mg of which are D-glucose or urine sugar), citric acid (0.5 g) and other organic acids, as well as certain vitamins (C, B₁₂ etc.). The following inorganic ions are present: Na⁺ (5.9 g), K⁺ (2.7 g), NH₄⁺ (0.8 g), Ca²⁺ (0.5 g), Mg²⁺ (0.4 g); Cl⁻ (8.9 g), PO₄³⁻ (4.1 g), SO₄⁻² (2.4 g). The dry content is between 50 and 72 g. *Inter alia*, alkylfurans, ketones, lactones, pyrrole, allyl isothiocyanate, and dimethyl sulfone have been recognized as volatile components of urine. Most of the volatile components are molecules having a molar mass below about 1000 g/mol and a high vapor pressure.

Volatile components of urine have also been investigated by, *inter alia*, A. Zlatkis et al. (Anal. Chem. Vol. 45, 763ff.). It is also well-known that consumption of asparagus results in an increase of the concentration of organic sulfur-containing compounds in human urine (R.H. Waring, *Xenobiotika*, Vol. 17, 1363ff.). In patients who are subject to specific diets and generally, in patients who ingest specific

05701564-120700

medications, or in elderly individuals with decreasing kidney function, the urine may include malodorous substances. Patients suffering from urine incontinence have an increased secretion of ureases which convert the urea contained in urine, thereby liberating toxic ammonia. Also, a pathological change is well-known which is referred to as fish smell syndrome. It results from an increased secretion of quaternary ammonium compounds.

Previous approaches of achieving an odor reduction in incontinence products are based on reducing the concentration of free ammonia. Basically, there are two approaches to this end: preventing additional production of ammonia from urea degradation by suitable urease inhibitors (A. Norberg et al., Gerontology, 1984, 30, 261ff.), or by protonating free ammonia and binding thereof in the form of a carboxylate ammonium salt. This method is disadvantageous in that essentially, merely ammonia and other nitrogen-containing components can be controlled. Malodorous compounds lacking basic groups, e.g. thiols, are still capable of entering the vapor space.

It is well-known to those skilled in the art that certain hollow molecules, also referred to as endohedral or concave molecules, are capable of incorporating other, mostly smaller, so-called guest molecules, thereby forming a host-guest complex. Such complex formation has an effect on the chemical and physical properties of both guest and host molecule. These hollow-forming molecules include the cyclodextrins.

Cyclodextrins are formed during starch degradation by *Bacillus macerans* or *Bacillus circulans* under the action of cyclodextrin glycosyl transferase. They are comprised of 6, 7, 8 or 9 glucose units α -1,4-linked to form a ring (α -, β - or γ -cyclodextrins). They are capable of entrapping hydrophobic guest molecules in varying amounts up to saturation ("molecular encapsulation"), e.g. gases, alcohols or hydrocar-

09701564 "120700

bons. The use of cyclodextrins as host molecule is reported comprehensively in the work of J. Szejtli (Cyclodextrin Technology, Kluwer Academic Publishers, 1988).

Also, the production of polymers containing cyclodextrins is already known. Thus, EP-A-0,483,380 obtains cyclodextrin-containing polymers by copolymerizing cyclodextrins bearing aldehyde groups with polyvinyl alcohol.

Crosslinked, water-swellaable, hydrophilic bead polymers made of hydroxyalkylcyclodextrins and epichlorohydrin or polyepoxide type crosslinkers are known from US-A-5,360,899. These crosslinkers involve a carcinogenic potential and therefore, such products cannot be used in hygiene articles. These cyclodextrins immobilized by polymerization are used as packing and separating material in chromatographic separation columns.

Furthermore, water-swellaable, hydrophilic bead polymers made of cyclodextrins bearing glycidyl or methacrylate groups and optionally other comonomers such as hydroxyethyl acrylate are known from US-A-5,357,012. Likewise, these cyclodextrins immobilized by polymerization are used as packing and separating material in chromatographic separation columns.

DE-A-195 20 989 describes covalent binding of reactive cyclodextrin derivatives having at least one nitrogen-containing heterocycle to polymers bearing at least one nucleophilic group. Polymers linked to cyclodextrins according to this method must have nucleophilic groups such as OH, NH, or SH groups. Also, polymerizable cyclodextrin derivatives are mentioned which, after suitable modification, are copolymerized with other monomers, e.g. ethylenically unsaturated compounds. As noted in this publication, the products according to the above-mentioned US patent specifications US 5,357,012 and US 5,360,899 involve the drawback that cyclo-

09701564 "120700

dextrin incorporation is difficult to control in spatial terms and that cyclodextrins fixed inside the polymers are no longer available for utilization. The use of polymers, which include cyclodextrin derivatives, as superabsorbing materials is not mentioned.

Inter alia, the use of cyclodextrins in hygiene products is known from EP-A-806,195, WO 94/22501, and WO 94/22500. Therein, the cyclodextrins are employed to absorb odors. In those cases where the cyclodextrins or cyclodextrin complexes are not bound to the powdered absorbent, demixing during storage or transportation of the hygiene articles may occur. As a result, the effectiveness of the cyclodextrins as odor absorbent may be lost due to demixing between absorbent and cyclodextrins.

To achieve improved adhesion on powdered absorbents, WO 94/22501 teaches addition of polyethylene glycols or other linear polymers to cyclodextrin in a "melt" or in solution and subsequent spraying on the powdered absorbent. However, as is well-known to those skilled in the art, linear polymers have a marked tendency to "thread" into the cyclodextrin cavity, which fact is advantageously utilized in supramolecular chemistry in order to produce e.g. rotaxans or catenanes (cf. the documents US 5,538,655; G. Wenz, Angew. Chem. 1994, 106, 851). Typically, the linear polymers have a molecular weight (m.w.) of more than 200. Also, suitable polymers are e.g. polyethylene glycol (PEG), polypropylene oxide (PEO) and polyethyleneimine. Multiple cyclodextrins can be threaded on a linear polymer chain; Harada et al. (J. Org. Chem. 58, 1993, 7524-28) report that 20 cyclodextrins can be threaded on a polyethylene glycol having an average molecular weight of 2000 g/mol. Therefore, the process described in WO 94/22501 is particularly disadvantageous, because the cyclodextrin cavities after such a polyethylene glycol pretreatment are no longer quantitatively available for absorbing malodorous compounds.

09701564 120700

The invention therefore is based on the object of providing polymer products capable of absorbing water or aqueous liquids, and capable of binding malodorous organic compounds such as occurring e.g. in urine or other fluids secreted from the body, and methods of producing same.

The polymer products should not involve the drawbacks of prior art and enable a preferably uniform, marked reduction of gaseous, malodorous compounds released during use. Moreover, a largely stable dispersion of the deodorant component in the absorbent should be achieved, i.e., demixing prior to and during use should be avoided as much as possible. In addition, binding of the deodorant component should not be effected by using carcinogenic or otherwise hazardous substances. Furthermore, the effectiveness of the deodorant component in the absorbent should be independent of its location, i.e., whether inside the polymer or at the surface thereof.

According to the invention, said object is accomplished by providing polymers based on crosslinked monomers bearing optionally partially neutralized acid groups, which polymers have cyclodextrins and/or derivatives thereof bound ionically and/or covalently and/or incorporated therein.


As a result of the inventive binding to the preferably powdered polymer, the cyclodextrin component can be extracted by the liquid to be absorbed to only a lesser extent, or, in the dry state, undergoes demixing to only a lesser extent. Despite the intimate linkage with the crosslinked absorber bearing acid groups, the polymer according to the invention surprisingly shows excellent absorption of odors which is even enhanced compared to unbound cyclodextrin. In particular, the absorbent polymers exhibit high absorption of odors even in those cases where the cyclodextrin is fixed inside the absorber. This can be established by an effective reduction in the gas concentration of malodorous substances.

09701564-120700

Moreover, the polymer products of the invention are excellently suited for incorporating active substances, and when used, these active substances can optionally be released in a controlled fashion. By incorporation in the absorbents of the invention, the stability of sensitive active substances is markedly improved.

According to the invention, α, β, γ type cyclodextrins and derivatives thereof are suitable.

The cyclodextrins have the following recurring structure:



The anhydroglucose units are linked in a cyclic, glycosidic fashion to form rings, wherein the residues R_1 through R_3 are the same or different, represent H or C_1-C_4 alkyl, and α -cyclodextrin: $n = 6$, β -cyclodextrin: $n = 7$, γ -cyclodextrin: $n = 8$, δ -cyclodextrin: $n = 9$. In cyclodextrin derivatives, n different substituents per residue (R_1-R_3) are possible which may be the same or different.

Above all, those derivatives are possible which permit chemical linkage by ionic or covalent binding to the monomer bearing acid groups or to the corresponding polymer. Covalent linkages preferably are via C-C bonds as, for example, with cyclodextrin derivatives having ethylenically unsaturated groups incorporated covalently in the polymer chain already during polymerization of the monomers. For example, such groups are (meth)acrylic, (meth)allyl and vinyl groups. According to the invention, however, covalent linkage of the

cyclodextrin component to the polymer of ethylenically unsaturated monomers is also possible subsequent to polymerization via ether, amide or ester groups.

Ionic binding of the cyclodextrin derivatives can be effected using anionic or cationic groups, with cationic groups being preferred. Frequently, it is advantageous when the cyclodextrin molecules have multiple substitutions with ionic groups. Examples of anionic groups are carboxylate, sulfate and sulfonate groups. Examples of cationic groups are quaternary groups containing nitrogen.

Ionic cyclodextrins can be produced by reacting cyclodextrin derivatives with reactive compounds such as chloroacetic acid, sodium chloroacetate, maleic acid, maleic anhydride, and succinic anhydride. In an aqueous solution, these reaction products, e.g. carboxymethylcyclodextrin, carry a negative charge in a basic medium due to the carboxylate group.

Cyclodextrin derivatives to be used according to the invention and having at least one nitrogen-containing heterocycle can be produced according to the teaching of DE-A-195 20 98, A1, the disclosure of which is hereby incorporated by reference. In this way, cyclodextrin derivatives can be obtained, which include another group active towards nucleophilic groups. These derivatives can undergo direct reaction with polymers bearing nucleophilic groups. Examples of nucleophilic groups are -OH, -NH or -SH groups.

Other chemically modified cyclodextrins to be used according to the invention can be obtained as described in A.P. Croft and R.A. Bartsch, Tetrahedron Vol. 39, No. 9, pp. 1417-1473. They are obtained by reacting nitrogen-containing compounds having at least one functional group capable of reacting with the hydroxyl groups of the cyclodextrins to form ether, ester or acetal groups.


09704564 "120700

Cationic cyclodextrins such as described in Ch. Roussel, A. Favrou, Journal of Chromatography A, 704 (1995), 67-74, are particularly preferred. They are obtained by reacting cyclodextrin with e.g. N-(3-chloro-2-hydroxypropyl)-N,N,N-trimethylammonium chloride. The cyclodextrins described in the above publication have a degree of substitution of 0.2.

The ionic cyclodextrins including at least one nitrogen-containing aliphatic residue, which can be used according to the invention, may also be produced e.g. according to the methods described in US 3,740,391; 4,153,585 and 4,638,058. The disclosure of the above-mentioned publications is hereby incorporated by reference.

For example, N,N-dimethylaminoethyl (meth)acrylate, N,N-dimethylaminopropyl (meth)acrylate, N,N-dimethylaminoethyl(meth)acrylamide, and N,N-dimethylaminopropyl(meth)acrylamide, or the quaternary derivatives thereof obtained by reaction with alkyl halides may be mentioned as suitable monomers. Preferably, N,N-dimethylaminoethyl acrylate (ADAME or ADAME-quat.) and N,N-dimethylaminopropylacrylamide (DIMAPA or DIMAPA-quat.) are employed.

Here, the compound of formula I undergoes reaction:



wherein $\text{R}^1 = \text{H}, \text{CH}_3$,
 $\text{R}^2 = \text{C}_2-\text{C}_4$ alkylene group,
 $\text{R}^3 = \text{H}, \text{C}_1-\text{C}_4$ alkyl group,
 $\text{X} = \text{O}, \text{NH}$,
 $\text{Y} = \text{Cl}, \text{SO}_4$.

The average degree of substitution (DS value) per anhydroglucose unit for substituents containing nitrogen can

be determined according to methods known from literature using elemental analysis as described e.g. in US 5,134,127 and US 3,453,257 for substituents containing sulfur or nitrogen. When using the synthetic methods described in US 3,740,391 and 4,153,585, the DS value can be varied within wide limits.

3 hydroxyl groups per anhydroglucose unit of a cyclodextrin are capable of undergoing further reaction. Therefore, the degree of substitution e.g. in case of β -cyclodextrin can be between 0.05 and 3 at maximum. A degree of substitution below 0.05 indicates that a mixture of non-modified cyclodextrin and chemically modified cyclodextrin is present.

According to the invention, the degree of substitution (DS) of the cyclodextrin derivatives is 0.005 - 2, preferably 0.05 - 1.5.

In addition to the above-mentioned groups required for binding to the polymer, the cyclodextrins may also contain other substituents having no reactivity towards the polymer. For example, these include reaction products of cyclodextrins with alkylating agents, e.g. C_1 - C_{22} alkyl halides, e.g. methyl chloride, ethyl chloride, butyl chloride, butyl bromide, benzyl chloride, lauryl chloride, stearyl chloride, or dimethyl sulfate, or reaction products of cyclodextrins with alkylene oxides such as ethylene oxide, propylene oxide, butylene oxide, or styrene oxide.

The amount of cyclodextrin or derivatives thereof to be employed according to the invention is 0.01-50 wt.-%, preferably 0.1-30 wt.-%, more preferably 0.5-10 wt.-%, relative to the total amount of polymer.

Well-known processes are possible for polymerizing the polymers of the invention optionally having superabsorbent properties, e.g. bulk polymerization, solution polymer-

09701564-120700

ization, spray polymerization, inverse emulsion polymerization, and inverse suspension polymerization.

Preferably, a solution polymerization is performed using water as solvent. The solution polymerization may be conducted in a continuous or batchwise fashion. The prior art includes a broad spectrum of possible variations with respect to concentration conditions, temperatures, type and amount of initiators and of secondary catalysts. Typical processes have been described in the following patent specifications: US 4,286,082; DE 27 06 135, US 4,076,663, DE 35 03 458, DE 40 20 780, DE 42 44 548, DE 43 23 001, DE 43 33 056, DE 44 18 818 which hereby are incorporated as disclosure of the process according to the invention.

Preferably, aliphatic, optionally substituted C_2-C_{10} , preferably C_2-C_5 carboxylic acids or sulfonic acids, such as acrylic acid, methacrylic acid, crotonic acid, isocrotonic acid, maleic acid, fumaric acid, itaconic acid, vinylacetic acid, vinylsulfonic acid, methallylsulfonic acid, 2-acrylamido-2-methyl-1-propanesulfonic acid, as well as the alkali and/or ammonium salts or mixtures thereof are possible as ethylenically unsaturated monomers containing acid groups. It is preferred to use acrylic acid and its alkali and/or ammonium salts and mixtures thereof. Furthermore, it is also possible to use monomers being hydrolyzed to form acid groups as late as subsequent to the polymerization, e.g. the corresponding nitrile compounds.

In order to modify the polymer properties, up to 40 wt.-% of monomers other than the monomers containing acid groups, which are soluble in the aqueous polymerization batch, such as acrylamide, methacrylamide, acrylonitrile, (meth)allyl alcohol ethoxylates, and mono(meth)acrylic acid esters of polyhydric alcohols or ethoxylates can optionally be used.

002021-49570460

Minor amounts of crosslinking monomers having more than one reactive group in their molecules are copolymerized together with the above-mentioned monomers, thereby forming partially crosslinked polymer products which are no longer soluble in water but merely swellable. Bi- or multifunctional monomers, e.g. methylenebisacryl- or -methacrylamide, or ethylenebisacrylamide may be mentioned as crosslinking monomers, and also, allyl compounds such as allyl (meth)acrylate, alkoxyated allyl (meth)acrylate reacted preferably with from 1 to 30 mol of ethylene oxide units, triallyl cyanurate, maleic acid diallyl ester, polyallyl esters, tetraallyloxyethane, triallylamine, tetraallylethylenediamine, allyl esters of phosphoric acid or phosphorous acid, and also, the N-methylol compounds of unsaturated amides such as methacrylamide or acrylamide and the ethers derived therefrom, as well as esters of polyols and alkoxyated polyols with unsaturated acids, such as diacrylates or triacrylates, e.g. butanediol or ethylene glycol diacrylate, polyglycol di(meth)acrylates, trimethylolpropane triacrylate, di- and triacrylate esters of trimethylolpropane preferably oxyalkylated (ethoxylated) with 1 to 30 mol alkylene oxide, acrylate and methacrylate esters of glycerol and pentaerythritol, and of glycerol and pentaerythritol preferably oxyethylated with 1 to 30 mol ethylene oxide. It is preferred to use triallylamine, acrylates of polyhydric alcohols or alkoxyates thereof, and methallyl alcohol acrylates or alkoxyates thereof. The ratio of crosslinking monomers is from 0.01 to 3.0 wt.-%, preferably from 0.05 to 2.0 wt.-%, and more preferably from 0.05 to 1.5 wt.-%, relative to the total weight of the monomers.

The optional neutralization of the acidic monomers according to the polymerization process of the invention can be performed in various ways. On the one hand, according to the teaching of US 4,654,039, the polymerization may be conducted directly with the acidic monomers, with neutralization being effected subsequently in the polymer gel. Preferably, the acid groups of the monomers are already neutralized to

20-95%, preferably 50-80% prior to polymerization, in which case they are present as sodium and/or potassium and/or ammonium salts at the time polymerization is begun. It is preferred to use those bases for neutralization which do not adversely affect the subsequent polymerization. It is preferred to use sodium or potassium hydroxide solution and/or ammonia, with sodium hydroxide solution being particularly preferred; addition of sodium carbonate, potassium carbonate or sodium bicarbonate may have an additional positive effect as taught in US 5,314,420 and US 5,154,713. Before initiating the polymerization in this adiabatic solution polymerization, the partially neutralized monomer solution is cooled to a temperature of below 30°C, preferably below 20°C. The other polymerization processes comply with the temperatures known from prior art as apparent from the literature below.

The polymer products of the invention may optionally contain water-soluble natural or synthetic polymers as a basis for grafting in amounts up to 30 wt.-%. *Inter alia*, these include partially or completely saponified polyvinyl alcohols, starch or starch derivatives, cellulose or cellulose derivatives, polyacrylic acids, polyglycols, or mixtures thereof. The molecular weights of the polymers added as basis for grafting must be adapted to the circumstances of the polymerization conditions. In the event of an aqueous solution polymerization, for example, it may be necessary for viscosity reasons to employ low to medium molecular weight polymers, whereas this factor plays a minor role in a suspension polymerization.

In addition to polymers obtained by crosslinking polymerization of partially neutralized acrylic acid, those are preferably used which are obtained by employing starch or polyvinyl alcohol as graft basis.

The polymerization process of the invention can be initiated by various conditions, e.g. by irradiating with

09701564-120700

radioactive, electromagnetic or ultraviolet radiation, or by a redox reaction of two compounds, e.g. sodium hydrogen sulfite with potassium persulfate, or ascorbic acid with hydrogen peroxide. The thermally induced decomposition of a so-called free-radical initiator such as azobisisobutyronitrile, sodium peroxodisulfate, t-butyl hydroperoxide, or dibenzoyl peroxide is suitable as well. Furthermore, a combination of some of the above-mentioned polymerization initiators is possible.

Preferably, the polymer products of the invention are produced according to two methods:

According to the first method, the partially neutralized acrylic acid is converted to a gel by means of free-radical polymerization in aqueous solution and in the presence of crosslinkers and optional polymer additives, which gel is subsequently crushed and dried until a powdered, flowable state is reached, milled, and screened to the desired particle size. The solution polymerization may be conducted in a continuous or batchwise fashion. The patent literature includes a broad spectrum of possible variations with respect to concentration conditions, temperatures, type and amount of initiators, as well as a variety of secondary crosslinking options. Typical processes have been described in the following patent specifications: US 4,076,663; US 4,286,082; DE 27 06 135, DE 35 03 458, DE 35 44 770, DE 40 20 780, DE 42 44 548, DE 43 23 001, DE 43 33 056, DE 44 18 818, the disclosure of which is hereby incorporated by reference.

The inverse suspension and emulsion polymerization process may also be used to produce the polymer products of the invention. According to this process variant, an aqueous, partially neutralized solution of acrylic acid is dispersed in a hydrophobic organic solvent using protective colloids and/or emulsifiers, and the polymerization is initiated using free-radical initiators. The crosslinkers are either dis-

09701564-120700

Using the process of subsequent surface crosslinking, the polymer products according to the invention are improved in their pattern of properties, particularly in their absorption of liquid under pressure, so that the well-known phenomenon of "gel blocking" is suppressed, where slightly swollen polymer particles adhere to each other, thereby impeding further absorption of liquid and distribution of liquid in the absorbent articles. In this secondary crosslinking, the carboxyl groups of the polymer molecules are crosslinked at the surface of the polymer particles at elevated temperature using crosslinking agents. *Inter alia*, methods of secondary crosslinking have been described in the following publications: DE 40 20 780, EP 317,106 and WO 94/9043. According to the invention, all those surface crosslinking agents known to a person skilled in the art from US 5,314,420, page 8, lines 3-45, may be employed advantageously in combination with a crosslinker used during polymerization or a combination of crosslinkers. As a rule, these compounds contain at least two functional groups capable of reacting with carboxylic acid or carboxyl groups. Alcohol, amine, aldehyde, and carbonate groups are preferred and also, crosslinker molecules having multiple different functions are employed. Preferably, polyols, polyamines, polyaminoalcohols, and alkylene carbonates are used. Preferably, one of the following crosslinking agents is used: ethylene glycol, diethylene glycol, triethylene glycol, polyethylene glycol, glycerol, polyglycerol, propylene glycol, diethanolamine, triethanolamine, polypropylene glycol, block copolymers of ethylene oxide and propylene oxide, sorbitan fatty acid esters, ethoxylated sorbitan

fatty acid esters, trimethylolpropane, ethoxylated trimethylolpropane, pentaerythritol, ethoxylated pentaerythritol, polyvinyl alcohol, sorbitol, ethylene carbonate, propylene carbonate. It is particularly preferred to use polyols and ethylene carbonate as surface crosslinking agents. The crosslinking agent is employed in an amount of from 0.01 to 30 wt.-%, preferably 0.1-10 wt.-%, relative to the polymer to be crosslinked.

Following polymerization, the polymer product is dried, milled, screened for the respective grain fraction favorable in application-technical terms, and subsequently subjected to surface crosslinking. In some cases, however, it has proven beneficial to add the surface secondary crosslinkers at an early stage prior to drying the polymer gel or prior to crushing the partially or predominantly dried polymer. Secondary crosslinking to be performed according to the invention has been described in US 4,666,983 and DE 40 20 780 which hereby are incorporated by reference. Advantageously, the secondary crosslinker frequently is added in the form of a solution in water, organic solvents or mixtures thereof, particularly in those cases where low amounts of secondary crosslinking agent are used. Suitable mixing apparatus for applying the secondary crosslinking agent are, e.g., Patterson-Kelley mixers, DRAIS turbulence mixers, Lödige mixers, Ruberg mixers, screw mixers, pan mixers, and fluid-bed mixers, as well as continuously operated vertical mixers wherein the powder is mixed at a rapid frequency using rotating knives (Schugi mixer). Once the surface crosslinker has been mixed with the crosslinked polymer, heating to temperatures of from 60 to 250°C, preferably from 135 to 200°C, and more preferably from 150 to 185°C is effected in order to perform the surface crosslinking reaction. The time period of the heat treatment is limited by the risk of destroying the desired pattern of properties of the superabsorbent polymer product as a result of heat damage.

00402749510260

Depending on the type of use, various screening fractions are employed for processing the polymer products as superabsorbers, e.g. between 100 and 1000 μm and preferably between 150 and 850 μm for diapers. In general, this grain fraction is produced by milling and screening prior to and/or subsequent to secondary crosslinking.

According to the process of the invention, the cyclodextrins or derivatives thereof are employed as substance or dissolved in a solvent. A preferred solvent is water, but mixtures of water and organic solvents such as ethyl alcohol, acetone are also used.

The addition of the cyclodextrin component can be effected at various process stages in the production of the polymer products according to the invention. The amount of cyclodextrins or derivatives thereof is 0.01-50 wt.-%, preferably 0.1-30 wt.-%, and more preferably 0.5-10 wt.-%, relative to the amount of polymer product.

Thus, addition to the monomer solution is possible, where the cyclodextrin or its derivative is added directly to the aqueous monomer solution prior to the polymerization thereof. In case the polymer product of the invention is produced by suspension polymerization, it is also possible to pre-charge all or part of the cyclodextrin in the oil phase and meter the monomer solution thereto. Where only a part of the cyclodextrin is pre-charged, the remainder can be introduced via the monomer solution.

It is also possible to apply the cyclodextrin component onto a non-dried polymer gel, where the cyclodextrin or its derivative as substance or dissolved in water and/or an organic solvent is applied onto the crushed polymer gel, preferably by spraying and mixing.

00402749510260

However, it is also possible to dry and crush the polymer gel initially, and subsequently apply the cyclodextrin or its derivative as substance or dissolved in water and/or an organic solvent onto the powder. The resulting product immediately can be processed further or dried to remove solvents.

The cyclodextrin component may also be added onto the crushed and dried absorbent material during surface crosslinking of the polymer product. Suitable mixing apparatus for applying the crosslinking agent and the cyclodextrin component are e.g. Patterson-Kelley mixers, DRAIS turbulence mixers, Lödige mixers, Ruberg mixers, screw mixers, pan mixers, and fluid-bed mixers, as well as continuously operated vertical mixers wherein the powder is mixed at a rapid frequency using rotating knives (Schugi mixer).

Also, the cyclodextrin component can be applied onto the crushed, already surface-crosslinked polymer product. In this process variant, according to the invention, preferably ionically modified cyclodextrins as substance or dissolved in water and/or an organic solvent are sprayed onto the preferably powdered polymer, followed by evaporating the solvent.

According to the process of the invention, the cyclodextrin component may also be introduced at various stages of the production process, so as to optionally optimize its effect. In this way it is possible, for example, to polymerize a non-modified cyclodextrin together with the monomer solution and fix an ionically modified cyclodextrin on the surface of the polymer during surface crosslinking.

It is also possible to bind the cyclodextrin component to the polymer in an additional surface crosslinking.

Using the methods according to the invention, final products are obtained wherein the cyclodextrin or its deriva-

00701564.120700

tive is incorporated in the synthetic polymer in such a way that the amount of cyclodextrin extractable with water is significantly less than the amount actually contained in the final product. In the products according to the invention, the extractable percentage of cyclodextrins is below 85% of the amount present in the product, preferably 60%, and more preferably 45%.

Owing to their excellent absorptive capacity, the polymer products of the invention are suitable as absorbents which, compared to powdered absorbents including no cyclodextrin or derivative thereof, exhibit improved absorption of malodorous compounds.

The polymers according to the invention find use e.g. in hygiene articles capable of absorbing body fluids such as urine, or in the packaging sector, e.g. meat and fish products, where they absorb large amounts of aqueous liquids and body fluids such as urine or blood, with swelling and formation of hydrogels. The polymer products of the invention are incorporated directly as powders in constructions for absorbing liquids, or previously fixed in foamed or non-foamed sheet materials. For example, such constructions for absorbing liquids are diapers for babies, incontinence articles or absorbent inserts in packaging units for foodstuffs.

Moreover, the absorbents of the invention were found to be excellently suited for incorporating active substances. The stability of sensitive active substances, e.g. with respect to oxidative degradation, is substantially improved as a result of incorporation in the absorbents of the invention.

Furthermore, the polymers according to the invention find use in plant breeding and in pest control in agriculture. In plant breeding, the polymers in the vicinity of plant roots provide for sufficient supply of liquid and pre-

In pest control, the polymers can incorporate single active substances or a combination of multiple active substances which in use are released in a controlled fashion in terms of time and amount.

Test methods used on polymers according to the invention:

$$EA(CD) = \frac{\text{Concentration (CD) found}}{\text{Theoretical concentration (CD)}}$$

EA(CD): extractable percentage of cyclodextrin.

0.1 g of powdered polymer product is added with 2 ml of an aqueous solution (including 5 wt.-% ethanol) of malodorous compound, and this is sealed in a 5 ml test vessel. This is allowed to stand at 40°C for 20 minutes, and the content of malodorous compound in the vapor space above the liquid is determined quantitatively against a blank using headspace GC.

Comparative Example 1 according to patent applications WO 94/22500 and WO 94/22501

9.850 g of a commercially available absorbent (Favor®, company Stockhausen GmbH) is mixed thoroughly with 0.15 g of solid β -cyclodextrin (beta-W7-cyclodextrin, technical grade, by Wacker company). Thereafter, the extractable amount of cyclodextrin is determined according to the specified test method.

$$EA = 93\%$$

Comparative Example 2 according to patent applications WO 94/22500 and WO 94/22501

40 g of polyethylene glycol (m.w. 3000) is melted at elevated temperature. 40 g of cyclodextrin is added thereto, and the mixture is homogenized. 9.40 g of a commercially available powdered absorbent (Favor®, company Stockhausen GmbH) is sprayed with 0.6 g of the cyclodextrin/polyethylene glycol solution, mixed thoroughly and cooled to room temperature. Thereafter, the extractable amount of cyclodextrin is determined according to the specified test method.

EA = 89%

A) An aqueous solution of acrylic acid (29.3 wt.-%) is mixed with 1.2 wt.-%/monomer of a polyglycol acrylate cross-linker mixture and partially neutralized to 60 mole-% using a 50% sodium hydroxide solution with stirring and cooling. The solution is cooled to 7-8°C and purged with nitrogen for about 20 minutes. Following addition of aqueous solutions of sodium persulfate, hydrogen peroxide and a water-soluble azo initiator, the polymerization is initiated with ascorbic acid, whereupon a significant rise in temperature to more than 90°C occurs. A gel-like product is obtained.

- B) 50 g of the dried and milled polymer from A) screened to 150-800 μm is wetted with a solution of 0.5 g of ethylene carbonate, 2 g of water and 4 g of acetone in a plastic vessel with vigorous stirring and mixed thoroughly using a commercially available household hand mixer (Krupps company). Subsequently, the wetted polymer is heated in an oven at a temperature of 180°C for 30 minutes, thereby undergoing surface crosslinking.
- C) The procedure is as described in A). In addition, however, 5 g of cyclodextrin is added to the monomer solution. A gel-like product is obtained, the further processing of which is effected as described in B).
- D) The gel free of cyclodextrin, which has been obtained in A), is immersed in a 80°C hot solution in a beaker, consisting of 10 g of cyclodextrin and 23.3 g of water, until the solution has completely permeated into the polymer gel. Subsequently, the gel is willowed and dried at 150°C.

EA = 27%, determined according to the specified test method.

E) 50 g of the dried and milled polymer from D) screened to 150-800 μm is wetted with a solution of 0.5 g of ethylene carbonate, 2 g of water and 4 g of acetone in a plastic vessel with vigorous stirring and mixed thoroughly using a commercially available household hand mixer (Krups company). Subsequently, the wetted polymer is heated in an oven at a temperature of 180°C for 30 minutes.

The extractable percentage, EA = 8%, determined according to the specified test method, is clearly lower as a result of surface crosslinking.

Example 2

50 g of the willowed, dried and milled polymer from Example 1 A) screened to 150-800 μm is wetted with a solution of 0.5 g of ethylene carbonate, 1.5 g of non-modified cyclodextrin, and 8.5 g of water in a plastic vessel with vigorous stirring and mixed thoroughly using a commercially available household hand mixer (Krups company). For surface crosslinking, the wetted polymer subsequently is heated in an oven at a temperature of 175°C for 25 minutes.

EA = 80%, determined according to the specified test method.

Example 3

F) In a 500 ml three-necked round bottom flask, 113.4 g of β -cyclodextrin is suspended in 200 g of deionized water and 8 g of an aqueous sodium hydroxide solution (50%). This suspension is heated to boiling until all of the above is dissolved. With vigorous stirring, 34.4 g of an aqueous solution of DIMAPA-quat. (60%) is added dropwise over 30 min, and this is stirred under reflux for another 5 hours. The solution is cooled to 5°C, and a pH of 7 is adjusted using hydrochloric acid. The precipitate is filtrated and washed with water. Following drying of the

filter residue, the DS value is determined to be 0.005 using elemental analysis. 50 g of the willowed, dried and milled polymer from Example 1 B) screened to 150-800 mm is wetted with a solution of 0.5 g of ethylene carbonate, 1.5 g of cyclodextrin derivative according to F), and 7.3 g of water in a plastic vessel with vigorous stirring and mixed thoroughly using a commercially available household hand mixer (Krupps company). For surface cross-linking, the wetted polymer subsequently is heated in an oven at a temperature of 175°C for 25 minutes.

EA = 40%, determined according to the specified test method.

Determination of the gas concentration of malodorous compounds

Superabsorbers made of polyacrylic acid with a degree of neutralization of 60% and 70%, respectively, and subjected to secondary surface crosslinking were modified in a second secondary surface crosslinking according to the procedure of Example 3, using various cyclodextrins. The amount of cyclodextrin can be inferred from the following Table. In the measurement of malodorous substances, a polymer with no cyclodextrin was tested as a blank according to the specified test procedure, and the gas concentration of malodorous substance found was set 100%. Samples containing cyclodextrin were subsequently tested and the gas concentration of malodorous substance determined.

Odorous substance: Ethylfuran.

Wt.-% CD	Cyclodextrin derivative	Reduction of ethylfuran concentration in the gaseous space
10##	β -Cyclodextrin	72%
3##	β -Cyclodextrin	63%
3##	α -Cyclodextrin	68%

##: Absorber having 60% neutralization of the acid groups

As can clearly be seen, the gas concentration of volatile substances dissolved in water is reduced upon absorption by the cyclodextrin-containing polymers of the invention.

In analogy to ethylfuran, an odorous substance containing sulfur was tested.

In addition, the effect of pure cyclodextrin (with no polymer) was monitored. As can be seen, cyclodextrin in the polymer of the invention from a content as low as 3% on achieves a marked reduction in the gas concentration of the sulfur-containing compound.

Doping with furfurylmercaptane:

Wt.-% CD	Cyclodextrin or CD derivative	Reduction of furfurylmercaptane concentration in the gaseous space
10#	β -Cyclodextrin	42%
3#	β -Cyclodextrin	51%
3#	α -Cyclodextrin	65%
10##	β -Cyclodextrin	46%
3##	β -Cyclodextrin	18%
3##	α -Cyclodextrin	28%
1.5#	Monochlorotriazinyl- β -cyclodextrin	42%
3#	Monochlorotriazinyl- β -cyclodextrin	49%
100	β -Cyclodextrin	57%
100	α -Cyclodextrin	64%

#: Absorber having 70% neutralization of the acid groups

##: Absorber having 60% neutralization of the acid groups

The polymers of the invention develop excellent effectiveness when the cyclodextrin is entrapped in the polymers:

Polymer of Example	CD ratio [wt.-%]	CD derivative	Reduction of furfurylmercaptane concentration in the gaseous space [%]
1 E	1.5	non-modif.	72
1 E	3	non-modif.	55
3	3	of Ex. 3F	49

002021"49510260

1. An absorbent polymer based on optionally partially neutralized, monoethylenically unsaturated monomers bearing acid groups, the surface of which polymer has been subjected to secondary crosslinking subsequent to polymerizing, characterized in that the polymer has cyclodextrins and/or cyclodextrin derivatives bound covalently and/or ionically and/or incorporated therein.
2. The polymer according to claim 1, characterized in that the polymer includes from 0.01 to 50 wt.-%, preferably from 0.1 to 30 wt.-%, more preferably from 0.5 to 10 wt.-% of cyclodextrins and/or cyclodextrin derivatives, relative to the polymer.
3. The polymer according to claim 1 or 2, characterized in that a maximum of 85 wt.-% of the amount of cyclodextrins and/or cyclodextrin derivatives in the polymer is extractable.
4. The polymer according to claim 3, characterized in that the extractable amount is 60 wt.-% at maximum, preferably 45% at maximum.
5. The polymer according to any of claims 1 to 4, characterized in that the polymer is constituted up to 40 wt.-% of monoethylenically unsaturated monomers other than the monomers bearing acid groups.
6. The polymer according to any of claims 1 to 5, characterized in that the polymer has from 0.05 to 3 wt.-% of a crosslinking monomer incorporated by polymerization.

7. The polymer according to any of claims 1 to 7, characterized in that the polymer has 30 wt.-% of a water-soluble, natural or synthetic polymer incorporated therein by polymerization and/or graft polymerization.
8. The polymer according to any of claims 1 to 7, characterized in that the polymer has been subjected to surface crosslinking using from 0.1 to 10 wt.-%, relative to the polymer, of a crosslinker component.
9. The polymer according to any of claims 1 to 8, characterized in that the polymer contains α -, β -, or γ -cyclodextrins or derivatives thereof as cyclodextrins or derivatives thereof.
10. The polymer according to any of claims 1 to 9, characterized in that the cyclodextrins or cyclodextrin derivatives are covalently bound to the polymer via ethylenically unsaturated groups.
11. The polymer according to any of claims 1 to 9, characterized in that the cyclodextrins or cyclodextrin derivatives are ionically bound to the polymer via carboxylate, sulfate, sulfonate, or quaternary amino groups.
12. The polymer according to claim 11, characterized in that the cyclodextrins or cyclodextrin derivatives are bound to the polymer in a cationic fashion.
13. A process for producing the polymers according to any of claims 1 to 12 by free-radical polymerization of an aqueous solution of the ethylenically unsaturated, optionally partially neutralized monomer bearing acid groups, optionally up to 40 wt.-% of further monoethylenically unsaturated comonomers, crosslinking monomers, and optionally up to 30 wt.-% of a water-soluble natural or synthetic polymer, optional isolation, crushing, and

drying of the polymer, characterized in that the cyclodextrin and/or cyclodextrin derivative is already contained in the polymer during secondary surface crosslinking of same, or the polymer having undergone surface crosslinking is treated with an ionic cyclodextrin derivative.

14. The process according to claim 13, characterized in that the cyclodextrin and/or cyclodextrin derivative is incorporated prior to or during polymerization of the monomers and/or applied on an optionally obtained hydrogel and/or on optionally milled and dried polymer prior to or during surface crosslinking of the polymer.
15. The process according to any of claims 13 to 14, characterized in that the cyclodextrin or cyclodextrin derivative is employed as substance or as a solution.
16. Use of the polymers according to any of claims 1 to 12 as an absorbent for aqueous liquids, preferably in absorbing body fluids, in optionally foamed sheet materials, in packaging materials, in plant breeding, and as soil improver.
17. The use of polymers according to claim 16 in hygiene articles.
18. Use of the polymers according to any of claims 1 to 12 as a vehicle and/or stabilizer for active substances or fertilizers being released optionally in a delayed fashion.

ABSTRACT

The invention relates to absorbent polymers based on optionally partially neutralised, monoethylenically unsaturated, acid group-carrying monomers. The surfaces of said polymers are re-cross-linked. The inventive polymers also have cyclodextrines and/or cyclodextrine derivatives which are covalently and/or ionically bonded and/or included therein.

00701564-120700

Declaration, Power Of Attorney and Petition

Page 1 of 3

WE (I) the undersigned inventor(s), hereby declare(s) that:

My residence, post office address and citizenship are as stated below next to my name,

We (I) believe that we are (I am) the original, first, and joint (sole) inventor(s) of the subject matter which is claimed and for which a patent is sought on the invention entitled

Water-absorbing polymers with supramolecular hollow molecules, method for
producing them and use of the same

the specification of which

☐ is attached hereto.

☐ was filed on _____ as
Application Serial No. _____
and amended on _____.

☒ was filed as PCT international application

Number PCT/EP99/03705 ✓
on 28.05.1999 ,
and was amended under PCT Article 19
on _____ (if applicable).

We (I) hereby state that we (I) have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

We (I) acknowledge the duty to disclose information known to be material to the patentability of this application as defined in Section 1.56 of Title 37 Code of Federal Regulations.

We (I) hereby claim foreign priority benefits under 35 U.S.C. § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate, or § 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed. Prior Foreign Application(s)

Application No.	Country	Day/Month/Year	Priority Claimed
198 25 486.5	GERMANY	08.06.1998 ✓	<input checked="" type="checkbox"/> Yes <input type="checkbox"/> No
_____	_____	_____	<input type="checkbox"/> Yes <input type="checkbox"/> No
_____	_____	_____	<input type="checkbox"/> Yes <input type="checkbox"/> No
_____	_____	_____	<input type="checkbox"/> Yes <input type="checkbox"/> No

2-00 HERRMANN, Edgar
NAME OF SECOND JOINT INVENTOR

Edgar Herrmann
Signature of Inventor

X 16.10.2000
Date

Residence: Kempener Str. 26
D-41334 Nettetal, GERMANY DEX

Citizen of: GERMANY ✓

Post Office Address: same as above

3-00 ISSBERNER, Jörg
NAME OF THIRD JOINT INVENTOR

Jörg Issberner
Signature of Inventor

28.08.2000
Date

Residence: Im Stillen Winkel 17
D-47804 Krefeld, GERMANY DEX

Citizen of: GERMANY ✓

Post Office Address: same as above

4-00 KERSTEN, Dagmar
NAME OF FOURTH JOINT INVENTOR

D. Kersten
Signature of Inventor

X 19.10.00
Date

Residence: Uerdinger-Str. 53,
D-40668 Meerbusch, GERMANY DEX

Citizen of: GERMANY ✓

Post Office Address: same as above

5-00 MERTENS, Richard
NAME OF FIFTH JOINT INVENTOR

X Richard Mertens
Signature of Inventor

X 29.09.2000
Date

Residence: Dahlerdyk 116a
D-47803 Krefeld, GERMANY DEX

Citizen of: GERMANY

Post Office Address: same as above

600 WERNER, Georg

NAME OF SIXTH JOINT INVENTOR

Signature of Inventor

Date

OCT 10²⁵ 2000

NAME OF SEVENTH JOINT INVENTOR

Signature of Inventor

Date

NAME OF EIGHTH JOINT INVENTOR

Signature of Inventor

Date

NAME OF NINTH JOINT INVENTOR

Signature of Inventor

Date

Residence: Kirchplatz 24
Dresdener Str. 7

D-47918 Tönisvorst, GERMANY DEX

Citizen of: GERMANY ✓

Post Office Address: same as above

Residence: _____

Citizen of: _____

Post Office Address: _____

Residence: _____

Citizen of: _____

Post Office Address: _____

Residence: _____

Citizen of: _____

Post Office Address: _____

We (I) hereby claim the benefit under Title 35, United States Code, § 119(e) of any United States provisional application(s) listed below.

_____ (Application Number)	_____ (Filing Date)
_____ (Application Number)	_____ (Filing Date)

We (I) hereby claim the benefit under 35 U.S.C. § 120 of any United States application(s), or § 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. § 112, I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR § 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application.

Application Serial No.	Filing Date	Status (pending, patented, abandoned)
_____	_____	_____
_____	_____	_____
_____	_____	_____

And we (I) hereby appoint: Norman F. Oblon, Reg. No. 24,618; Marvin J. Spivak, Reg. No. 24,913; C. Irvin McClelland, Reg. No. 21,124; Gregory J. Maier, Reg. No. 25,599; Arthur I. Neustadt, Reg. No. 24,854; Richard D. Kelly, Reg. No. 27,757; James D. Hamilton, Reg. No. 28,421; Eckhard H. Kuesters, Reg. No. 28,870; Robert T. Pous, Reg. No. 29,099; Charles L. Gholz, Reg. No. 26,395; Vincent J. Sunderdick, Reg. No. 29,004; William E. Beaumont, Reg. No. 30,996; Steven B. Kelber, Reg. No. 30,023; Robert F. Gnuse, Reg. No. 27,295; Jean-Paul Lavalleye, Reg. No. 31,451; Stephen G. Baxter, Reg. No. 32,884; Martin M. Zoltick, Reg. No. 35,745; Robert W. Hahl, Reg. No. 33,893; Richard L. Treanor, Reg. No. 36,379; Steven P. Weihrouch, Reg. No. 32,829; John T. Goolkasian, Reg. No. 26,142; Marc R. Labgold, Reg. No. 34,651; Richard L. Chinn, Reg. No. 34,305; Steven E. Lipman, Reg. No. 30,011; Carl E. Schlier, Reg. No. 34,426; James J. Kulbaski, Reg. No. 34,648; Catherine B. Richardson, Reg. No. 39,007; Richard A. Neifeld, Reg. No. 35,299; J. Derek Mason, Reg. No. 35,270; Surinder Sachar, Reg. No. 34,423; Sharon E. Crane, Reg. No. 36,113; Christina M. Gadiano, Reg. No. 37,628; Jeffrey B. McIntyre, Reg. No. 36,867; and Paul E. Rauch, Reg. No. 38,591; our (my) attorneys, with full powers of substitution and revocation, to prosecute this application and to transact all business in the Patent Office connected therewith; and we (I) hereby request that all correspondence regarding this application be sent to the firm of OBLON, SPIVAK, McCLELLAND, MAIER & NEUSTADT, P.C., whose Post Office Address is: Fourth Floor, 1755 Jefferson Davis Highway, Arlington, Virginia 22202.

We (I) declare that all statements made herein of our (my) own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

1-00 BRUHN, Christoo
NAME OF FIRST ~~SOLE~~ INVENTOR

Residence: Robinienweg 39
D-47447 Moers, GERMANY DEX

Christo Bruhn
Signature of Inventor

Citizen of: GERMANY ✓

Post Office Address: same as above

11.10.00
Date